

ABSTRACT OF THE DISCLOSURE

A reactive polyester polyol is described that is obtainable by half ester formation starting from at least one dicarboxylic anhydride and at least one hydroxyl group carrying, saturated or unsaturated fatty acid and/or a respective ester, in particular castor oil and/or ricinoleic acid, as well as final esterification by at least one polyol.

09916485.073001